

# Product Data Sheet

520-(9)-04/14



Makers of Fine Paint Since 1962

ISSUED: 11 April 2014

Page 1 of 2

## 520 Implement Enamel



USE



THINNER/CLEAN

F-200  
F-205  
T-14

APPLICATION



RECOAT



HAZARD



*A fast drying general purpose spraying enamel of extra high gloss and good durability. Ideally suited for all industrial finishing where an air-dry coating is required.*

**USES:** In all industrial areas where a high gloss air drying finish is suitable. 520 Implement Enamel is ideal for finishing of agricultural machinery, stillages, waste bins and trailers

**SURFACE PREPARATION:** All surfaces should be clean, dry and free from oil and grease. Use 131 Superbond on bright and non-ferrous surfaces. Steel surfaces should be primed with suitable anti corrosive primers such as the 131 Superbond or 291 Satin Primer systems.

**APPLICATION:** Stir thoroughly until product is uniform. 520 Implement Enamel is best suited to spray application. Apply a light tack coat paying special attention to edges and corners, allow a short flash time (5 minutes) and then apply one full coat. 520 Implement Enamel may also be brushed on small areas such as handrails or pipes.

Conventional Spray: 1.5 mm to 2mm Fluid nozzle at an air pressure of 45 to 50 psi (300-350 kPa) is recommended. Thin approximately 30% with F-200 Reducer.

Airless Spray: Recommended Tip size is 11 to 13 thou. Thin approximately 10-15% with F-200 Reducer.

Electrostatic Spray: 520 Implement Enamel can be sprayed electrostatically. Please contact Topline Paint.

Brush: When brushing, Mineral Turps may be used sparingly to increase flow.

In hot conditions replace F-200 with F-205 to slow drying, improve flow and prevent dry spray.

**CLEAN UP:** F-200 Reducer, F-205 Reducer or T-14 Gunwash.

**DRYING:** Touch dry 30 minutes and dry to handle in 3-4 hours @ 25°C. Re-coat after 6 hours.

**COLOUR:** White, Black, Clear and an extensive colour range. Custom matching available.

**FINISH:** High gloss.

**COVERAGE:** Theoretical coverage 10-12m<sup>2</sup>/Litre at typical 30 µm dry film thickness. Volume Solids 44% (typical)

**PACK SIZES:** 4 Litre, 20 Litre.

**VEHICLE TYPE:** Modified alkyd.

**PIGMENT TYPE:** Lightfast pigments appropriate for that colour.

### FILM PROPERTIES:

|                     |  |                     |       |
|---------------------|--|---------------------|-------|
| Solvent Resistance  | Fair.  | Chemical Resistance | Fair. |
| Abrasion Resistance | Good.  | Impact Resistance   | Good. |
| Heat Resistance     | Good up to 90°C. White and pastel colours will show some yellowing at higher temperatures. | Flexibility         | Good. |

**TOPLINE PAINT PTY LTD**

**33 ALDERSHOT ROAD, LONSDALE, SOUTH AUSTRALIA 5160.**

Telephone: (08) 8384 1188

Fax: (08) 8326 1824

E-mail: admin@toplinepaint.com.au

Customers need to appreciate that as Topline Paint cannot control the conditions under which our products are used, we therefore are unable to guarantee suitability or accuracy in every situation. If any doubt exists, do check with our technical people. Before large-scale use always test on a small sample and ascertain suitability. No warranties express or implied are made. The risks and liability arising from handling, storage, use and compliance with legal restrictions, rests with the buyer.





## 520 Implement Enamel

### PRECAUTIONS:

*The following information is a general guide only. Industrial users (ie where the product is being used in the workplace) are legally required to have available a Material Safety Data Sheet on this product. If you are unsure if you have an MSDS on this product please contact Topline Paint and one will be provided.*

**Safety Directions:** **KEEP OUT OF REACH OF CHILDREN – DO NOT SWALLOW.** Breathing the vapour is harmful and may cause lung irritation. Avoid contact with skin and eyes. Wear suitable, protective clothing, eye protection and impervious gloves when mixing and using. Handling and usage of this product must be carried out under well ventilation conditions that prevent inhalation of vapours, dust or mist. Use the appropriate breathing equipment (refer to Aust Stand. 1716) when ventilation is restricted. Keep containers closed when not in use. Eliminate any source of ignition (open fires, pilot lights, furnaces, spark producing switches etc.) as this product is flammable. **DO NOT SMOKE.** Take precautionary measures against static discharges. Used clean up rags may spontaneously ignite. To avoid ignition immerse in water or store in a sealable glass container.

**First Aid Instructions:** If affected by inhalation, remove to fresh air. If breathing difficulty persists or occurs later, consult a doctor. If swallowed, **DO NOT INDUCE VOMITING** drink plenty of water and seek medical advice. Contact a Doctor of Poisons Information Centre (Phone 131126). If skin contact occurs, remove contaminated clothing and wash skin thoroughly with soap and water. If irritation occurs seek prompt medical advice. Immerse contaminated clothing in water for 24 hours and do not use until laundered. In case of eye contact, hold eyes open and flood with running water for at least 15 minutes seek medical advice.

**Leaks, Spills and Disposal:** To prevent ignition of fumes product shut off all ignition sources. Contain or shut off leak if safe to do so. For large leaks or spills of volatile, flammable product, use respiratory protection, protective apparel and footwear. Spills should be absorbed either with rags (small spill) or dry sand/earth (large spill). In the case of flammable product spillage, use spark free implements to place rags or absorbed material into a solvent resistant container. Cover with water for 24 hours before disposal. **DO NOT** pour left over product down the drain – retain it in marked sealed container for future use or disposal through chemical waste collection programs. Dried empty cans can be recycled and should be disposed of via council steel recycling facilities.

**Fire:** Use foam and breathing apparatus. Avoid breathing products of combustion.

**Hazard:** The coloured square at the top of page 1 is provided for a quick reference as to the hazard level of a product. Blue refers to coatings with low hazard (eg water based wall paints). Yellow refers to medium hazard products such as QD enamels, which contain solvents, are flammable and need respirators for vapour protection. Red refers to products with special hazards such as isocyanate cured two pack finishes